




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61B 17/04	A1	(11) International Publication Number: WO 98/00065 (43) International Publication Date: 8 January 1998 (08.01.98)
<p>(21) International Application Number: PCT/US97/11359</p> <p>(22) International Filing Date: 27 June 1997 (27.06.97)</p> <p>(30) Priority Data: 08/671,902 28 June 1996 (28.06.96) US</p> <p>(71) Applicant: UNITED STATES SURGICAL CORPORATION [US/US]; 150 Glover Avenue, Norwalk, CT 06856 (US).</p> <p>(72) Inventors: ROBY, Mark, S.; 11 Grace Lane, Killingworth, CT 06419 (US). JIANG, Ying; 34 Grandview Terrace, North Haven, CT 06473 (US). BOBO, John, S.; 24 River Colony, Guilford, CT 06437 (US). REINPRECHT, Jon, T.; 236 Oakville Avenue, Waterbury, CT 06708 (US).</p> <p>(74) Agent: FARBER, Mark; United States Surgical Corporation, 150 Glover Avenue, Norwalk, CT 06856 (US).</p>	<p>(81) Designated States: AL, AM, AU, AZ, BA, BB, BG, BR, BY, CA, CN, CU, CZ, EE, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, RO, RU, SD, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>	
(54) Title: ABSORBABLE MIXTURE AND COATINGS FOR SURGICAL ARTICLES FABRICATED THEREFROM		
		
(57) Abstract		
<p>Absorbable mixtures are fabricated from a predominant component of fatty acid ester mixed with a copolymer comprising a predominant amount of epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer of other bioabsorbable monomers. These mixtures are useful in forming coating for surgical articles, including multifilament sutures.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**ABSORBABLE MIXTURE AND COATINGS
FOR SURGICAL ARTICLES FABRICATED THEREFROM**

TECHNICAL FIELD

Absorbable materials fabricated from mixtures of caprolactone containing copolymers and esters of fatty acids, and more particularly coatings for surgical articles made totally or in part therefrom, including coatings for multifilament sutures, are provided.

BACKGROUND OF THE INVENTION

Synthetic absorbable multifilament sutures such as Dexon, Vicryl, and Polysorb commercially available from Davis & Geck (Danbury, Connecticut), Ethicon, Inc. (Sommerville, New Jersey), and United States Surgical Corporation (Norwalk, Connecticut), respectively, are well known in the industry.

Suture coatings for synthetic absorbable sutures containing caprolactone are well known, see for example U.S. Patents 4,624,256; 4,190,720; 4,582,052; 4,605,730; 4,700,704; 4,705,820; 4,788,979; 4,791,929; 4,994,074; 5,047,048; 5,100,433; 5,133,739; 5,352,515. Suture coatings containing esters of fatty acids are also known see for example U.S. Patents 5,032,638, 4,711,241, 4,705,820, and 4,027,676.

In the early 1970's Ethicon introduced uncoated Vicryl; see for example Horton C.E., Adamson J.E., Mladick R.A., et al: "Vicryl Synthetic Absorbable Sutures"; Am Surg, Dec. 1974, pp 729-31. However, this uncoated braided multifilament caused tissue trauma (tissue drag) and handling problems. As a result, in the late 1970's a Vicryl suture coated with a glycolide/lactide copolymer blended with calcium stearate was introduced; see for example Saunder's R.A. et al: "Coated Vicryl Suture in Extraocular Muscle Surgery". Ophthalmic Surg 10:13-8, July 1979 and Kobayashi H et al. "Coated Polyglactin 910- a New Synthetic Absorbable Suture". Jpn J Surg 11(6):467-75, Nov. 1981. U.S. Patent

4,201,216 discloses a glycolide/lactide copolymer blended with calcium stearate as a suture coating.

Although calcium stearate was used as a component in the Vicryl suture coating; the manufacture and application of such a suture coating would require an impractical and uneconomical dip coating process because calcium stearate (a hydrophobic metal salt of a fatty acid) generally is insoluble. Therefore, a suture coating fabricated from materials that would dissolve in solution and thus obviate the necessity of using dip coating processes would provide great manufacturing advantages.

Another important feature of a suture coating is its ability to enhance the suture's handling characteristics, such as surgeon's throw, lubricity, knot run down and/or knot security. Although commercially available surgical sutures such as Polysorb have excellent handling characteristics; it would be advantageous to provide a coated suture exhibiting even better surgeon's throw, lubricity, knot run down, and/or knot security properties.

SUMMARY OF THE INVENTION

It has now been found that such a coating for absorbable surgical articles may be formed from the mixture of a copolymer containing caprolactone with an ester of a fatty acid.

Preferably, mixtures useful in forming the aforementioned coatings include an ester of a fatty acid as a predominant component. A "predominant component" is a component which is present in an amount greater than about 50 weight percent. A "minor component" is a component which is present in an amount up to about 50 weight percent. The minor component comprises copolymers containing caprolactone.

Particularly useful caprolactone containing copolymers are "star" copolymers obtained by polymerizing a major amount of epsilon-caprolactone and a minor amount of another bioabsorbable monomer polymerizable therewith in the presence of a polyhydric alcohol initiator.

Particularly useful fatty acid esters include calcium stearyl lactylate. Since such fatty acid esters are soluble,

coatings fabricated from mixtures of such fatty acid esters and caprolactone containing polymers need not be applied to surgical articles by the undesirable dip coating process.

5 In a particularly useful embodiment the mixture may be applied to braided multifilament sutures. Preferably mixtures useful in this embodiment comprise at least about 52 percent fatty acid ester, the remainder being caprolactone containing copolymer. Applied to a suture, the coating composition results in advantageous improvement in one or more properties of the suture,
10 e.g., knot security, surgeon's throw, lubricity, knot run down, and/or knot repositioning.

BRIEF DESCRIPTION OF THE DRAWINGS

15 Figure 1 is a perspective view of a coated suture attached to a needle described herein.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

It has been found that fatty acid esters and caprolactone containing polymers can advantageously be mixed to form a
20 composition (with fatty acid esters as the predominant component thereof) useful in coating surgical sutures.

Suitable caprolactone containing copolymers include copolymers which may be synthesized by well known conventional polymerization techniques; see, for example Principles of
25 Polymerization, George Odian, III Edition; 1991 pp.569-573, the contents of which are incorporated herein by reference.

Preferably, the caprolactone containing copolymer is obtained by polymerizing a major amount of epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer or mixture of
30 such monomers in the presence of a polyhydric alcohol initiator. The polymerization of these monomers contemplates all of the various types of monomer addition, i.e., simultaneous, sequential, simultaneous followed by sequential, sequential followed by simultaneous, etc.

35 The copolymer herein can contain from about 70 to about 98, and preferably from about 80 to about 95, weight percent epsilon-


caprolactone derived units, the balance of the copolymer being derived from the other copolymerizable monomer(s).

Suitable monomers which can be copolymerized with epsilon-caprolactone include alkylene carbonates such as trimethylene carbonate, tetramethylene carbonate, dimethyl trimethylene carbonate; dioxanones; dioxepanones; absorbable cyclic amides; absorbable cyclic ether-esters derived from crown ethers; hydroxyacids capable of esterification, including both alpha hydroxy acids (such as glycolic acid and lactic acid) and beta hydroxyacids (such as beta hydroxybutyric acid and gamma hydroxyvaleric acid); polyalkyl ethers (such as polyethylene glycol and polypropylene glycol and combinations thereof; with glycolide being a preferred monomer.

Suitable polyhydric alcohol initiators include glycerol, trimethylolpropane, 1,2,4-butanetriol, 1,2,6-hexanetriol, triethanolamine, triisopropanolamine, erythritol, threitol, pentaerythritol, ribitol, arabinitol, xylitol, N,N,N',N'-tetrakis(2-hydroxyethyl)ethylenediamine, N,N,N',N'-tetrakis(2-hydroxypropyl)ethylenediamine, dipentaerythritol, allitol, dulcitol, glucitol, altritol, iditol, sorbitol, mannitol, inositol, and the like; with mannitol being preferred.

The polyhydric alcohol initiator is generally employed in small amounts, e.g., from about 0.01 to about 5, and preferably from about 0.1 to about 3, weight percent of the total monomer mixture.

Suitable esters of fatty acids include esters of the formula:



wherein x is an alkaline-earth metal or ion thereof and R₁ is C₁₀ or greater alkyl, R₂ is H, or C₁-C₃ alkyl, R₃ is H, or C₁-C₃ alkyl, R₄ is H, or C₁-C₃ alkyl, R₅ is H, or C₁-C₃ alkyl, and n>1. Such suitable fatty acids include calcium, magnesium, aluminum, barium, or zinc stearyl lactylate; calcium, magnesium, aluminum, barium, or zinc palmityl lactylate; calcium, magnesium, aluminum, barium, or zinc oleyl lactylate; with calcium stearyl-2-lactylate (such

as the calcium stearoyl-2-lactylate commercially available under the tradename VERV from American Ingredients Co., Kansas City, Mo.) being preferred.

5 The caprolactone containing copolymer and the fatty acid ester are non-toxic; a mixture of the two is non-toxic as well.

The bioabsorbable mixture herein can be applied to a suture by any suitable process, e.g. passing the suture through a solution of the copolymer, e.g. in toluene, methylene chloride, etc., past a brush or other coating solution applicator, or past
10 one or more spray nozzles dispensing the suture coating solution. The suture wetted with the coating solution is subsequently passed through or held in a drying oven for a time and at a temperature sufficient to vaporize and drive off the solvent. If desired, the suture coating composition can optionally contain additional
15 components, e.g., dyes, antibiotics, antiseptics, growth factors, anti-inflammatory agents, etc.

While the coating composition herein can be applied to any type of suture, it is essentially intended for application to a braided suture, a preferred type of which is disclosed in U.S.
20 Patent No. 5,019,093. The amount of coating composition applied to a braided suture will vary depending upon the structure of the suture, e.g., the number of filaments, tightness of braid or twist, the size of the suture and its composition. Suitable coating levels range from about 0.3% to about 10% with about 0.5%
25 to about 5% being preferred.

The coated suture, suture 101, may be attached to a surgical needle 100 as shown in Fig. 1 by methods well known in the art. Wounds may be sutured by passing the needled suture through tissue to create wound closure. The needle preferably is then removed
30 from the suture and the suture tied. The coating advantageously enhances the surgeon's ability to pass the suture through tissue as well as to increase the ease and security with which he/she can tie the suture.

The following examples are given as an illustration of the
35 preparation of copolymers, blends and coatings described herein as well as of the preparation and superior characteristics of the

sutures described herein. It should be noted that the invention is not limited to the specific details embodied in the examples.

EXAMPLE 1

5 Dry glycolide (222g), epsilon-caprolactone (2000g), stannous octoate as catalyst (0.44g) and dry mannitol as initiator (2.2g) were mixed under N₂ for one hour. The mixture was heated in a reactor at a temperature of 160°C for 12 hours. The epsilon-caprolactone / glycolide star copolymer was then sampled.

10 1820g of toluene were mixed with 180 grams of the reaction product at 90°C for 2 hours under constant stirring, to form a solution.

EXAMPLE 2

15 1820g of toluene were mixed with 180 grams of calcium stearoyl lactylate (commercially available from American Ingredients Co., Kansas City, Missouri, under the tradename VERV) at 90°C for one hour under constant stirring to form a solution.

EXAMPLE 3

20 1000g of the solution of Example 1 were mixed with 1000 grams of the solution of Example 2 at 25°C for 10 minutes under constant stirring to form the coating solution.

EXAMPLE 4

25 A size 0 Polysorb surgical suture was drawn through a coating solution applicator which applied the coating solution of Example 3, at a level of about 3.1 percent by weight of the suture, to coat the suture with the coating solution.

30 After drying the sutures in an oven for 16 hours, performance characteristics of the sutures, e.g., Surgeon's Throw, Knot Reposition and Knot Security, were measured on a standard tie board.

COMPARATIVE EXAMPLE 1

This was a size 0 suture commercially available from Ethicon, Inc. (Sommerville, New Jersey) under the name Vicryl.

5

COMPARATIVE EXAMPLE 2

Trimethylene carbonate (hereinafter TMC) (1200 grams) and glycolide (2800 grams) were added to a reactor along with 0.4 grams of stannous octoate and about 7 grams to about 8 grams of diethylene glycol. The mixture was heated and placed at 160°C, with stirring under a nitrogen atmosphere for 5 hours. The TMC/glycolide copolymer was then sampled.

1820g of toluene were mixed with 180 grams of the TMC/glycolide copolymer for two hours to form a solution. The solution was then mixed with 2000g of the solution of Example 2 for 10 minutes hours under constant stirring to form a coating solution.

Then size 0 Polysorb suture was drawn through a coating applicator, which applied the TMC/glycolide containing coating solution at a level of about 1.3 percent by weight of the suture to coat the suture with the coating solution.

After drying the sutures under vacuum for 16 hours, performance characteristics of the sutures, e.g., Surgeon's Throw, Knot Reposition, and Knot Security, were measured on a standard tie board.

A tie board consists of a base on which two plates are perpendicularly affixed. These plates are parallel to one another on the base and are separated by a distance of at least 3 inches. Each plate contains two oppositely disposed openings, the distance between the openings on one plate being longer than that of the other plate. An elastic tube is passed through the openings on both plates to complete a loop which is then tied to secure the loop to the plates. The loop is in the general configuration of an isosceles triangle. To perform the Surgeon's Throw and Knot Reposition tests as described below, a suture is looped and tied around the elastic tube of the tie board and tied. The elastic tube exerts an outward force on the suture knot. This force

approximates the force exerted by living tissue on suture knots. Thus, the tie board is an effective means of evaluating the performance characteristics of surgical sutures.

The procedures for evaluating these performance
5 characteristics are described in Table I as follows:

TABLE I

10

PROCEDURES FOR MEASURING PERFORMANCE
CHARACTERISTICS OF COATED SUTURES

Performance
Characteristic

Test Procedure

Surgeon's Throw

A suture is looped around the elastic tubes of a tie board and tied with a surgeon's throw (a half hitch with an extra loop of the free end). The ends are pulled apart by hand and the suture loop pulls the elastic tubes of the tie board together. The ends of the suture are then released. If the tubes stay together for approximately ten seconds, the trial is counted as a "pass". If the surgeon's throw slips and the tubes move apart, the trial is counted as a "failure".

Knot Reposition

A suture is looped around the elastic tubes of a tie board and tied with two half hitches in the same direction (a granny knot). The free ends of the suture are pulled apart by hand. If the knot slips and the loop of the suture pulls the elastic tubes of the tie board together, the knot is said to reposition and the trial is counted as a "pass". If the suture breaks or if the knot locks in place and cannot be moved, the trial is counted as a "failure".

Knot Security

A 2cm loop is tied with a surgeon's square knot (1=1=1=1) securing the throws at 20% of the USP XXII knot strength for 2/0 nonabsorbable sutures (n=10 loops per group). The loop is placed next to a cloth-wrapped mandrel rotating at .5 rpm. The fixtures are secured to allow contact of the cloth material against the fourth throw or, top throw, of each knot. The cloth wrapping is moistened with 37°C water prior to the test and is periodically remoistened during the test. For each pass of the cloth across the knot (for a total of 100 passes), the knot is inspected for top throw security. For a knot to be considered secure, there must be no relaxation of the knot or loss of the fourth throw.

The test results are set forth in Table II below:

TABLE II
PERFORMANCE CHARACTERISTICS OF SUTURES

Example	Coating Level (%)	Surgeon's Throw (No. of passes/ 10 attempts)	Knot Reposition (No. of passes/ 10 attempts)	Knot Security (No. failures per 10 attempts)
Example 4	3.1	9	9	0
Com- parative Example 1 (Vicryl size 0 suture)	1.8	9	8	0
Com- parative Example 2 (size 0 polysorb suture coated with a mixture of VERV and a copolymer of TMC and glycolide	3.1	10	4	0

As the data in Table II illustrates, the suture coated with the mixture of fatty acid ester and caprolactone containing copolymer performs comparable to or better than commercially available Vicryl suture and shows substantially improved knot reposition over Comparative Example 2.

It will be understood that various modifications may be made to the embodiments disclosed herein. For example, although it is preferred to coat surgical sutures from the disclosed mixtures, a wide variety of surgical articles can be coated. These include but are not limited to clips and other fasteners, staples, pins, screws, prosthetic devices, drug delivery devices, meshes or fabrics, anastomosis rings, and other implantable devices. Therefore, the above description should not be construed as limiting, but merely as exemplifications of preferred embodiments. Those skilled in the art will envision other modifications within the scope and spirit of the claims appended hereto.

WHAT IS CLAIMED IS:

1. A surgical suture coating comprising:
 - a) a copolymer comprising a predominant amount of
5 epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer; and
 - b) a lactylate ester of a C₁₀ or greater fatty acid.
2. The surgical suture coating of claim 1 wherein the
10 copolymer component comprises a reaction product obtained by polymerizing a major amount of epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer in the presence of polyhydric alcohol as initiator.
3. The surgical suture coating of claim 2 wherein the other
15 copolymerizable monomer is selected from the group consisting of alkylene carbonates, dioxanones, dioxepanones, absorbable cyclic amides, absorbable cyclic ether-esters derived from crown ethers, hydroxyacids capable of esterification, and combinations thereof.
20
4. The surgical suture coating of Claim 3 wherein the other
copolymerizable monomer is selected from the group consisting of glycolide, lactide, p-dioxanone and trimethylene carbonate.
5. The surgical suture coating of Claim 3 containing from
25 about 80 to about 95 weight percent epsilon-caprolactone-derived units, the balance of the copolymer being derived from at least one other copolymerizable monomer.
6. The surgical suture coating of Claim 5 wherein the other
30 copolymerizable monomer is glycolide.
7. The surgical suture coating of Claim 2 wherein the
polyhydric alcohol initiator is selected from the group consisting
35 of glycerol, trimethylolpropane, 1,2,4-butanetriol, 1,2,6-hexanetriol, triethanolamine, triisopropanolamine, erythritol,

threitol, pentaerythritol, ribitol, arabinitol, xylitol, N,N,N',N'-tetrakis(2-hydroxy-ethyl)ethylenediamine, N,N,N',N'-tetrakis(2-hydroxypropyl) ethylenediamine, dipentaerythritol, allitol, dulcitol, glucitol, altritol, iditol, sorbitol, mannitol and inositol.

8. The surgical suture coating of Claim 7 wherein the polyhydric alcohol is employed in an amount of from about 0.5 to about 5 weight percent of the total monomer mixture.

9. The surgical suture coating of Claim 1 wherein the salt of a lactylate ester of a C₁₀ or greater fatty acid ester is selected from the group consisting of magnesium stearoyl lactylate, aluminum stearoyl lactylate, barium stearoyl lactylate, zinc stearoyl lactylate, calcium palmityl lactylate, magnesium palmityl lactylate, aluminum palmityl lactylate, barium palmityl lactylate, or zinc palmityl lactylate, calcium olelyl lactylate, magnesium olelyl lactylate, aluminum olelyl lactylate, barium olelyl lactylate, and zinc olelyl lactylate.

10. The surgical suture coating of Claim 1 wherein the salt of a lactylate ester of a C₁₀ or greater fatty acid is calcium stearoyl lactylate.

11. A suture coated with a composition fabricated from a blend of a up to about 50 weight percent of a copolymer the remainder being a lactylate ester of a C₁₀ or greater fatty acid selected from the group consisting of magnesium stearoyl lactylate, aluminum stearoyl lactylate, barium stearoyl lactylate, zinc stearoyl lactylate, calcium palmityl lactylate, magnesium palmityl lactylate, aluminum palmityl lactylate, barium palmityl lactylate, or zinc palmityl lactylate, calcium olelyl lactylate, magnesium olelyl lactylate, aluminum olelyl lactylate, barium olelyl lactylate, zinc olelyl lactylate and calcium stearoyl lactylate, said copolymer comprising the reaction product obtained by polymerizing a major amount of epsilon-caprolactone and a minor

amount of at least one other copolymerizable monomer in the presence of polyhydric alcohol as initiator.

5 12. The surgical suture of Claim 11 wherein the suture is a braided suture.

10 13. The surgical suture of Claim 11 wherein the suture is coated with a coating level ranging from about 0.5 to about 4 for size 3/0 suture and above; and from about 1 to about 10 for size 4/0 and below.

15 14. The surgical suture of Claim 11 wherein the coating comprises from about 5 to about 95 percent by weight of the copolymer component; the remainder being the salt of a lactylate ester of a C₁₀ or greater fatty acid.

20 15. The surgical suture of Claim 12 wherein the coating comprises from about 5 to about 95 percent by weight of the copolymer component; the remainder being calcium stearoyl lactylate.

16. An implantable medical device having a coating comprising a mixture of

25 a) a copolymer comprising a predominant amount of epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer; and

30 b) the salt of a lactylate ester of a C₁₀ or greater fatty acid selected from the group consisting of magnesium stearoyl lactylate, aluminum stearoyl lactylate, barium stearoyl lactylate, zinc stearoyl lactylate, calcium palmityl lactylate, magnesium palmityl lactylate, aluminum palmityl lactylate, barium palmityl lactylate, or zinc palmityl lactylate, calcium olelyl lactylate, magnesium olelyl lactylate, aluminum olelyl lactylate, barium olelyl lactylate, zinc olelyl lactylate and calcium
35 stearoyl lactylate.

17. The implantable medical device of claim 16 wherein said medical device is selected from the group consisting of clips, staples, pins, screws, prosthetic devices, anastomosis rings, and growth matrices.

5

18. A surgical suture coating comprising:

a) a copolymer comprising a predominant amount of epsilon-caprolactone and a minor amount of at least one other copolymerizable monomer; and

10

b) a salt of a lactylate ester of a C₁₀ or greater fatty acid selected from the group consisting of magnesium stearoyl lactylate, aluminum stearoyl lactylate, barium stearoyl lactylate, zinc stearoyl lactylate, calcium palmityl lactylate, magnesium palmityl lactylate, aluminum palmityl lactylate, barium palmityl lactylate, or zinc palmityl lactylate, calcium olelyl lactylate, magnesium olelyl lactylate, aluminum olelyl lactylate, barium olelyl lactylate, and zinc olelyl lactylate.

15

19. The surgical suture of Claim 18 wherein the coating comprises from about 5 to about 95 percent by weight of the copolymer component; the remainder being the salt of a lactylate ester of a C₁₀ or greater fatty acid.

20



FIG. 1

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/11359

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : A61B 17/04

US CL : 606/228

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 428/364, 378, 294; 606/228, 230, 231

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,380,780 A (OLSON) 10 January 1995, col. 2, lines 55-68; col. 3, line 40; and col. 4, lines 30-53.	1-8
A	US 5,609,609 A (OHSHIMA et al) 11 March 1997.	1-19
A	US 5,522,842 A (SHALABY) 04 June 1996.	1-19



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	*T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A document defining the general state of the art which is not considered to be of particular relevance	*X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E earlier document published on or after the international filing date	*Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L documents which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*& document member of the same patent family
*O document referring to an oral disclosure, use, exhibition or other means	
*P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

29 JULY 1997

Date of mailing of the international search report

05 SEP 1997

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

TINA T. D. PHAM

Telephone No. (703) 308-0824